

Test Report

Number: GZHT02307036


Report Ref:	GZHT02307036		
Date Received:	Jun 23, 2020	Date Issued:	Jun 30, 2020

Company Name:	3A MEDICAL PRODUCTS CO.,LTD YU AN INDUSTRIAL PARK, 230001 LIU AN PEOPLE'S REPUBLIC OF CHINA
Address:	
Contact Name:	邓颖

The Following Sample Was Submitted And Identified By/On Behalf Of The Applicant As:	
End Uses	: Medical Face Mask
Ratings	: Level 3
Sample Name	: Disposable Medical Mask With Ear Loops
Size	: 17.5x9.5cm
Colour	: Navy
Standard	: ASTM F2100-19 ^{e1}
Manufacturer	: 3A MEDICAL PRODUCTS
Brand	: 3A MEDICAL
Buyer	: Newline
Date received/ Test Started	: Jun 23, 2020
Ref	: 3A1003L3 皖械 20202140040 anhui food and drugadministstion of firearms production xu 20202140040 shanghai international holding crop.Gmbh (europe)

Test was conducted on specific items, at our client's request.

Prepared And Checked By:
For Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch



Lin Lin
General Manager



Page 1 Of 8

Ula / abbyqzeng

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, China

中国广州经济技术开发区科学城彩频路7号之二第1-8层02房、01房

101、
E201、E301、E401、E501、E601、E701、E801

Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663

3/F Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

中国广州经济技术开发区开发大道235号恒运大厦3楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode: 510730



Test Report

Number: GZHT02307036

Original Sample Photo



Prepared And Checked By:
For Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch

Lin Lin
General Manager

Ula / abbyqzeng



Page 2 Of 8

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, China

中国广州经济技术开发区科学城彩频路7号之二第1-8层02房、01房、101、

E201、E301、E401、E501、E601、E701、E801

Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663

3/F Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

中国广州经济技术开发区开发大道235号恒运大厦3楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode: 510730



Test Report

Number: GZHT02307036


Summary of testing:

With reference to following standard:

- ASTM F2100-19^{E1} Standard Specification for Performance of Materials Used in Medical Face Masks Level 3
- ASTM F2101-19 Standard Test Method for Evaluating the Bacterial Filtration Efficiency (BFE) of Medical Face Mask Materials, Using a Biological Aerosol of Staphylococcus aureus
- EN 14683:2019+AC:2019 Medical face masks – Requirements and test methods
- ASTM F2299/F2299M-17 Standard Test Method for Determining the Initial Efficiency of Materials Used in Medical Face Masks to Penetration by Particulates Using Latex Spheres
- ASTM F1862/F1862M-17 Standard Test Method for Resistance of Medical Face Masks to Penetration by Synthetic Blood
- 16 CFR Part 1610 Wearing Apparel Flammability

Materials Used in The Submitted Samples Were Found To Comply With The Requirements Of Above Standards As Specified in ASTM F2100-19^{E1} 9.1-9.5.

Prepared And Checked By:
For Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch



Lin Lin
General Manager



Page 3 Of 8

Ula / abbyqzeng

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, China

中国广州经济技术开发区科学城彩频路7号之二第1-8层02房、01房、101、

E201、E301、E401、E501、E601、E701、E801

Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663

3/F Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

中国广州经济技术开发区开发大道235号恒运大厦3楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode: 510730



Test Report

Number: GZHT02307036

Tests Conducted (As Requested By The Applicant)

1 Flammability Test (ASTM F2100-19^{e1}, Section 9.5, Testing Refer to 16 CFR Part 1610 -2008):

<u>As Received</u>		
X	Plain Surface	Raised Surface
Burn Direction : <input checked="" type="checkbox"/> Length <input type="checkbox"/> Width		Requirement Class 1
Prelim Plain Surface :		
Length: IBE		
Width: -		
Original* (seconds)		
1.	IBE	
2.	IBE	
3.	IBE	
4.	IBE	
5.	IBE	
6.	-	
7.	-	
8.	-	
9.	-	
10.	-	
Average : -		
Classification :	<input checked="" type="checkbox"/>	Class 1, Normal Flammability
	<input type="checkbox"/>	Class 2, Intermediate Flammability, Raised Surface
	<input type="checkbox"/>	Class 3, Rapid And Intense Burning
Explanation Of Flammability Results:		
IBE	Ignited but extinguished.	

* The disposable fabrics and garments need not to be refurbished in accordance with 16 CFR Part 1610.35 (a)(2).

Ula / abbyqzeng



Test Report

Number: GZHT02307036

Tests Conducted (As Requested By The Applicant)

2 Bacterial Filtration Efficiency (BFE)

As Per ASTM F2100-19^{E1} Standard Specification for Performance of Materials Used in Medical Face Masks Clause 9.1 and ASTM F2101-19 Standard Test Method for Evaluating the Bacterial Filtration Efficiency (BFE) of Medical Face Mask Materials, Using a Biological Aerosol of Staphylococcus aureus.

Test Item	Results (%)					Performance Requirement for Medical Face Mask (%)
	Specimen (1)	Specimen (2)	Specimen (3)	Specimen (4)	Specimen (5)	
Bacterial Filtration Efficiency (BFE)	>99.9	>99.9	99.9	>99.9	99.9	Level 3: ≥98

Remarks:

1. Biological Aerosol: Staphylococcus aureus (ATCC 6538).
2. Testing side: Outside of the test specimen was facing towards the challenge aerosol.
3. Test area: 78 cm²
4. Flow rate: 28.3 L/min
5. The average plate count results of the positive controls: 2400 CFU
6. The average plate count results of the negative controls: < 1 CFU
7. CFU = Colony Forming Unit

Ula / abbyqzeng

Page 5 Of 8

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, China

中国广州经济技术开发区科学城彩频路7号之二第1-8层02房、01房、101、

E201、E301、E401、E501、E601、E701、E801

Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663

Room 01, Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

中国广州经济技术开发区开发大道235号恒运大厦3楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode: 510730



Test Report

Number: GZHT02307036

Tests Conducted (As Requested By The Applicant)

- 3 Differential Pressure (ASTM F2100-19^{e1}, Section 9.2, Testing Refer to EN 14683:2019+AC:2019 Annex C):
Air flow: 8L/min, Test Area Diameter 25 mm, Test Area: 4.9 cm².

<u>Tested Sample</u>	<u>Result (mm H₂O/cm²)*</u>					<u>Performance Requirement for Medical Face Mask (mm H₂O/cm²)</u>
	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5	Level 3: < 6.0
Location 1	4.4	4.3	3.8	4.3	3.9	
Location 2	4.2	4.3	4.0	4.5	4.6	
Location 3	4.2	4.2	4.4	4.1	4.5	
Location 4	4.6	4.2	4.4	4.5	4.1	
Location 5	4.4	4.7	4.1	4.8	4.0	
Average	4.4	4.3	4.1	4.4	4.2	
* = All the locations were evenly taken from the main mask body.						

- 4 Sub-Micron Particulate Filtration (ASTM F2100-19^{e1}, Section 9.3, Testing Refer to ASTM F2299/F2299M-17):
Particle size in aerosol: 0.1 µm, Aerosol: PSL, Test area: 100 cm², Airflow: 5.33cm/s, Sampling time: 1 min.

Tested Sample/Component	Result (%)	Performance Requirement for Medical Face Mask (%)
Specimen (1)	98.0	Level 3: ≥ 98
Specimen (2)	98.8	
Specimen (3)	98.1	
Specimen (4)	98.9	
Specimen (5)	98.8	

Remark: Test was conducted by external provider

Ula / abbyqzeng



Test Report

Number: GZHT02307036

Tests Conducted (As Requested By The Applicant)

- 5 Resistance to Penetration by Synthetic Blood (ASTM F2100-19^{e1}, Section 9.4, Testing Refer to ASTM F1862/F1862M-17):
Synthetic blood surface tension: 0.040 N/m, Distance between blow head front end and target area: 300 mm, Artificial blood volumes: 2 mL, Test Pressure: 160mmHg, Velocity: 635 cm/s, Use a fixed target.

<u>Tested Sample/Component</u>	<u>Result</u>	<u>Performance Requirement for Medical Face Mask</u> Pass Pressure at Level 3: 160 mm Hg
Specimen (1)	None seen	
Specimen (2)	None seen	
Specimen (3)	None seen	
Specimen (4)	None seen	
Specimen (5)	None seen	
Specimen (6)	None seen	
Specimen (7)	None seen	
Specimen (8)	None seen	
Specimen (9)	None seen	
Specimen (10)	None seen	
Specimen (11)	None seen	
Specimen (12)	None seen	
Specimen (13)	None seen	
Specimen (14)	None seen	
Specimen (15)	None seen	
Specimen (16)	None seen	
Specimen (17)	None seen	
Specimen (18)	None seen	
Specimen (19)	None seen	
Specimen (20)	None seen	
Specimen (21)	None seen	
Specimen (22)	None seen	
Specimen (23)	None seen	

Ula / abbyqzeng

Page 7 Of 8

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, China

中国广州经济技术开发区科学城彩频路7号之二第1—8层02房、01房、101、

E201、E301、E401、E501、E601、E701、E801

Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663

Room 01, Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

中国广州经济技术开发区开发大道235号恒运大厦3楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode: 510730



Test Report

Number: GZHT02307036

Tests Conducted (As Requested By The Applicant)

Specimen (24)	None seen
Specimen (25)	None seen
Specimen (26)	None seen
Specimen (27)	None seen
Specimen (28)	None seen
Specimen (29)	None seen
Specimen (30)	None seen
Specimen (31)	None seen
Specimen (32)	None seen

Remark: Test was conducted by external provider

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.

Ula / abbyqzeng

Page 8 Of 8

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, China

中国广州经济技术开发区科学城彩频路7号之二第1-8层02房、01房、

101、E201、E301、E401、E501、E601、E701、E801

Tel: +86 20 8213 9001 Fax: +86 20 8208 9909 Postcode: 510663

3/F, Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

中国广州经济技术开发区开发大道235号恒运大厦3楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode: 510730

